



## Product Description

- Flexible, durable, breathable
- Hydrophobic - assists in mitigating CUI
- Constructed of type E needle felt fiberglass blanket impregnated with PTFE resins
- Maximum use temperature 650°C (1200°F) continuous
- Very good thermal conductivity
- Easy to handle, fabricate and install
- Dust generation is nil
- Small width rolls (of 8 mm thickness) can be spiral wrapped like tape on small diameter pipe
- Perfect for piping and equipment where insulation must remain dry
- PTFE-coated fiberglass provides enhanced chemical resistance of the glass
- Available in 4 thicknesses

## Physical Properties

Color	Grey	
Density	144 to 192 kg/m <sup>3</sup> (9 to 12 lb/ft <sup>3</sup> )	
Thickness	8, 16, 20, and 25 mm (0.32, 0.63, 0.78, 1 inch)	
Maximum Use Temp	649°C (1200°F)	
Hydrophobicity	Continuous up to 315°C (600°F)	
Standard Available Widths	<u>8 mm thick</u> 50 to 1820 mm (2 to 72 in.)	<u>16, 20, and 25 mm thick</u> 700 to 1820 mm (30 to 72 in.)

## Material Performance Data

Test Method	Performance	Value
ASTM C356	Linear Shrinkage Under Soaking Heat	<2% @ 649°C
ASTM C795	Corrosiveness over Austenitic SS	Passed
ASTM C1101	Classifying Flexibility	Resilient Flexibility
ASTM C1104	Water Vapor Sorption	<1% (by wt)
ASTM C1338	Fungi Resistance	Passed
ASTM C1763	Water Absorption by Immersion	Procedure B, <5%
ASTM C1511	Liquid Water Retention Post-submersion after heat aging per test method	<5%
ASTM E84	Surface Burning Characteristics	FSI=0 ; SDI=0

\* Third party test reports available upon request

Blanket Thickness (mm)	Roll Length Meter (ft)
8	~38.1 (125)
16	~19.8 (65)
20	~15.2 (50)
25	~13.7 (45)



## Thermal Performance per ASTM C177\*

Temperature (°C)	0	100	200	300	400	500	600
Thermal Conductivity (mW/mK)	32.5	43.4	55.7	71.2	85.2	102.5	133.4
Temperature (°F)	32	212	392	572	750	932	1112
Thermal Conductivity (Btu·in/hr·ft <sup>2</sup> ·°F)	0.23	0.30	0.39	0.49	0.59	0.71	0.93

\* Third party test reports available upon request

This information is given in good faith and is believed to be accurate. No expressed or implied warranty of any kind including those of merchantability or fitness for a particular purpose is made as to the performance of an installation. Super Insulation, LLC does not take any responsibility for misuse of these products and recommends testing before use.

6859 Renoir Avenue  
Baton Rouge, LA 70806



Tel: (225) 924-3221  
Fax: (225) 927-2918

Rev. 8  
February 2024